

No. : TJAT1709010826NM

Date : Oct 23, 2017

Page: 1 of 5

CUSTOMER NAME: ONERPRO TECHNOLOGIES CORP. ADDRESS: 5511, 11 Brunel Court, City Place, Toronto, Ontario M5V 3Y2

The following sample's information(s) was/ were submitted and identified on behalf of the client as:

| Sample Name        | : | : ONERPRO Paint Protection Film                            |  |
|--------------------|---|--|--|
| SGS Ref No.        | : | TJIN1709013449MR   |  |
| Date of Receipt    | : | Sep 25, 2017   |  |
| Testing Start Date | : | Sep 25, 2017   |  |
| Testing End Date   | : | Oct 13, 2017   |  |
| Test Result(s)     | : | For further details, please refer to the following page(s) |  |

Signed for and on behalf of SGS-CSTC Standards Technical Services(Tianjin) Co., Ltd

isa n

Lisa Jin Lab Supervisor



No. : TJAT1709010826NM

Date : Oct 23, 2017

Page: 2 of 5

#### **Report Declaration:**

The test samples were provided and confirmed by the customer in this report, the results contained in this test report do not relate to other samples of the same product. The manufacturer should ensure that all products manufactured are in conformity with the product sample in this report.

#### Manufacture Declaration or Comment:

None

#### Summary of Result(s):

| No. | Test Item         | Test Method  | Conclusion |
|-----|-------------------|--|------------|
| 1.  | 90º Peel Strength | ASTM D6252/D6252M-98(2011)<br>and client's requirement | See result |

Note: Pass: Meet the requirements Fail: Does not meet the requirements N/A: Not apply to the judgment




No. : TJAT1709010826NM

Date : Oct 23, 2017

Page: 3 of 5

Original Sample Photo:





No. : TJAT1709010826NM

Date : Oct 23, 2017

Page: 4 of 5

1. Test Item: 90º Peel Strength

Test Method: ASTM D6252/D6252M-98(2011) and client's requirement

Test Condition:

Specimen width: 25.5mm

Testing speed: 300mm/min

Lab Environmental Condition: 23  $\pm$  2  $^\circ\!\mathrm{C}$  , 50  $\pm$  5 % RH

Test Result:

| Test Item                  | Test Result             | Client's requirement    | Conclusion |
|----------------------------|-------------------------|-------------------------|------------|
| 90º Peel Adhesion Strength | 56.2 N/100mm            | \                       | \          |
|                            | No residual adhesive    | No residual adhesive    |            |
| Appearance                 | tape on the paint, no   | tape on the paint, no   | Pass       |
|                            | obvious change in paint | obvious change in paint |            |

Note:

1. The specimens preparation was completed by client.


2. Test specimens were cut from the sample.



No. : TJAT1709010826NM

- Date : Oct 23, 2017
- Page: 5 of 5

Test Photo:



Equipment Information:

| Equipment                    | Model      | Equipment No. | Calibration date | Next Calibration<br>date |
|------------------------------|------------|---------------|------------------|--------------------------|
| Universal Testing<br>Machine | Zwick Z010 | POL-022       | 2016-11-7        | 2017-11-6                |

\*\*\*\*\*\*\*\* End of report\*\*\*\*\*\*\*