



## TEST REPORT

No. : TJAT1709011682NM

Date : Oct 17, 2017

Page: 1 of 6

CUSTOMER NAME: ONERPRO TECHNOLOGIES CORP.

ADDRESS: 5511, 11 Brunel Court, City Place, Toronto, Ontario M5V 3Y2

The following sample's information(s) was/ were submitted and identified on behalf of the client as:

**Sample Name** : ONERPRO Paint Protection Film  
**Part No.** : H/R/S  
**SGS Ref No.** : GZIN1709047308MR  
**Date of Receipt** : Sep 29, 2017  
**Testing Start Date** : Sep 29, 2017  
**Testing End Date** : Oct 16, 2017  
**Test Result(s)** : For further details, please refer to the following page(s)

Signed for and on behalf of  
SGS-CSTC Standards Technical  
Services(Tianjin) Co., Ltd

.....  
Lisa Jin

Lab Supervisor



## TEST REPORT

No. : TJAT1709011682NM

Date : Oct 17, 2017

Page: 2 of 6

### Report Declaration:

The test samples were provided and confirmed by the customer in this report, the results contained in this test report do not relate to other samples of the same product. The manufacturer should ensure that all products manufactured are in conformity with the product sample in this report.

### Manufacture Declaration or Comment:

None

### Summary of Result(s):

No.	Test Item	Test Method	Conclusion
1.	Alkali Resistance	JIS K 5400-1990 Section 8.21	Pass
2.	Acid Resistance	JIS K 5400-1990 Section 8.22	Pass
3.	Salt-Water Resistance	JIS K 5400-1990 Section 8.23	Pass

**Note:**  
Pass: Meet the requirements  
Fail: Does not meet the requirements  
N/A: Not apply to the judgment


## TEST REPORT

No. : TJAT1709011682NM

Date : Oct 17, 2017

Page: 3 of 6

Original Sample Photo:



## TEST REPORT

No. : TJAT1709011682NM

Date : Oct 17, 2017

Page: 4 of 6

1. Test Item: Alkali Resistance

Test Method: JIS K 5400-1990 Section 8.21

Test Condition:


Immersion method, 24h, then keep at room temperature for 2h

Test Result:

Sample	Reagent	Result	Client's requirement	Conclusion
A	5w/V% Na <sub>2</sub> CO <sub>3</sub> (AR)	No visible damage	No visible damage	Pass

Note: Evaluation the appearance of tested sample after 2 hours at room temperature.

Test Photo:



Equipment Information:

Equipment	Model	Equipment No.	Calibration date	Next Calibration date
Electron Balance	PL2002	GZMR-AG-E125	2017-07-04	2018-07-03

## TEST REPORT

No. : TJAT1709011682NM

Date : Oct 17, 2017

Page: 5 of 6

2. Test Item: Acid Resistance

Test Method: JIS K 5400-1990 Section 8.22

Test Condition:


Immersion method, 24h, then keep at room temperature for 2h

Test Result:

Sample	Reagent	Result	Client's requirement	Conclusion
A	5w/V% H <sub>2</sub> SO <sub>4</sub> (AR)	No visible damage	No visible damage	Pass

Note: Evaluation the appearance of tested sample after 2 hours at room temperature.

Test Photo:



## TEST REPORT

No. : TJAT1709011682NM

Date : Oct 17, 2017

Page: 6 of 6

3. Test Item: Salt-Water Resistance

Test Method: JIS K 5400-1990 Section 8.23

Test Condition:


Immersion method, 96h, then keep at room temperature for 2h

Test Result:

Sample	Reagent	Result	Client's requirement	Conclusion
A	5w/V% NaCl(GR)	No visible damage	No visible damage	Pass

Note: Evaluation the appearance of tested sample after 2 hours at room temperature.

Test Photo:



Equipment Information:

Equipment	Model	Equipment No.	Calibration date	Next Calibration date
Electron Balance	PL2002	GZMR-AG-E125	2017-07-04	2018-07-03

\*\*\*\*\* End of report\*\*\*\*\*