

No.: TJAT1709010832NM

Date: Oct 16, 2017

Page: 1 of 5

CUSTOMER NAME: ONERPRO TECHNOLOGIES CORP.

ADDRESS: 5511, 11 Brunel Court, City Place, Toronto, Ontario M5V 3Y2

The following sample's information(s) was/ were submitted and identified on behalf of the client as:

Sample Name : ONERPRO Paint Protection Film

Part No. : H/R/S

SGS Ref No. : TJIN1709013436MR

Date of Receipt : Sep 25, 2017

Testing Start Date : Sep 25, 2017

Testing End Date : Oct 11, 2017

Test Result(s) : For further details, please refer to the following page(s)

Signed for and on behalf of SGS-CSTC Standards Technical Services(Tianjin) Co., Ltd

Lisa Jin

Lab Supervisor



No.: TJAT1709010832NM

Date: Oct 16, 2017

Page: 2 of 5

Report Declaration:

The test samples were provided and confirmed by the customer in this report, the results contained in this test report do not relate to other samples of the same product. The manufacturer should ensure that all products manufactured are in conformity with the product sample in this report.

Manufacture Declaration or Comment:

None

Summary of Result(s):

No.	Test Item	Test Method	Conclusion
1.	Light Ageing Test-UV Exposure	ASTM G154-16 Cycle1 & ASTM D2244-16	Pass

Note: Pass: Meet the requirements

Fail: Does not meet the requirements

N/A: Not apply to the judgment




No.: TJAT1709010832NM

Date: Oct 16, 2017

Page: 3 of 5

Original Sample Photo:





No.: TJAT1709010832NM

Date: Oct 16, 2017

Page: 4 of 5

1. Test Item: Light Ageing Test-UV Exposure

Test Method: ASTM G154-16 Cycle1 & ASTM D2244-16

Test Condition:

Exposure cycle:

ASTM G154-16 cycle 1 Lamp type: UVA-340

8h UV at (60±3) °C BPT, 0.89 W/(m²•nm)@340 nm

4h condensation at (50±3) ℃ BPT

Exposure duration: 240 h

Test Result:

Sample	Appearance	ΔE* _{ab}	Client's requirement	Conclusion
1	No visual change of film	-	No visual change of film	Pass
	-	0.15	-	-




No.: TJAT1709010832NM

Date: Oct 16, 2017

Page: 5 of 5

Test Photo:



Equipment Information:

Fauinment	Model	Equipment No.	Calibration date	Next Calibration
Equipment				date
QUV Accelerated	QUV/se	POL-020	2016-11-07	2017-11-06
Weathering Tester	QU V/Se			

******* End of report*******